

Rubber Chemicals for Elastomers

Accelerators

Dithiocarbamates						
Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Accelerator ZDEC	Zinc diethyl dithiocarbamate	14324-55-1	Secondary	Ultra Fast	1,2	Fastest dithiocarbamate
Accelerator ZDBC	Zinc dibutyl dithiocarbamate	136-23-2	Secondary	Ultra Fast	2	Next fastest to ZDEC
Ekaland™ ZBEC	Zinc dibenzyl dithiocarbamate	14726-36-4	Secondary	Ultra Fast	1,2	Slowest of all dithiocarbamates and a non-nitrosamine alternative
ZDEC>ZDBC>ZBEC						

Sulfenamides						
Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Kemai CBS	N-Cyclohexyl-2-benzothiazole sulfenamide	95-33-0	Primary	Fast	1,2,3	Fastest delayed action sulfenamide and is a non-nitrosamine alternative
Kemai DCBS	N,N-dicyclohexyl-2-benzothiazole sulfenamide	4979-32-2	Primary	Fast	3	Safest delayed action sulfenamide
CBS>DCBS						

Thiurams (sulfur bearing, except TMTM)

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Accelerator TETD	Tetraethylthiuram disulfide	97-77-8	Secondary	Fast	2,4	Next fastest Thiuram
Ekaland™ TMTM	Tetramethylthiuram monosulfide	97-74-5	Secondary	Fast	2,3	Next fastest of Thiurams compared to MET
Ekaland™ TBzTD	Tetrabenzylthiuram disulfide	10591-85-2	Secondary	Fast	2	Slowest rate versus TMTM and non-nitrosamine alternative
Ekaland™ DPTT	Dipentamethylene thiuram hexasulfide	971-15-3	Secondary	Fast	1,2	Sulfur bearing accelerator for most polymers; enhances heat stability and aging properties
TETD>TMTM>TBzTD>DPTT						

Thiazoles

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Kemai MBTS	2,2-Dithiobis (benzothiazole)	120-78-5	Primary	Semi-Fast	1,2,3	Slower than MBT. MBTS is used in polychloroprene for delayed action and is a non-nitrosamine alternative

Thioureas

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Ekaland™ ETU	Ethylene thiourea	96-45-7	Secondary	Medium Fast	1,2	Fastest thiourea used in polychloroprene, but can be used in EPDM as secondary
Ekaland™ DETU	N,N'-Diethylthiourea	105-55-5	Secondary	Medium Fast	4	Fast thiourea used in mercaptan modified polychloroprene and as secondary accelerator in EPDM
Ekaland™ DBTU	N,N'-Dibutylthiourea	109-46-6	Secondary	Medium Fast	5	Next fastest thiourea in polychloroprene
Ekaland™ DPTU	N,N'-Diphenylthiourea	102-08-9	Secondary	Medium Fast	1	Slowest thiourea for polychloroprene
ETU>DETU>DBTU>DPTU						

Phenoldisulfides

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Vultac®2	Poly-tert-amylphenol disulfide	68555-98-6	Secondary	Ultra Fast	7	Bleaching agent for rosins and rosin esters
Vultac® 3	Poly-tert-amylphenol disulfide	68555-98-6	Secondary	Ultra Fast	7	Nitrosamine-free vulcanizing agent
Vultac® 5	Mixture of poly-tert-amylphenoldisulfide and silica	68555-98-6 112926-00-8	Secondary	Ultra Fast	1	75% by weight of ground Vultac 3 mixed with silica gel
Vultac® 710	Mixture of poly-tert-amylphenoldisulfide and stearic acid	68555-98-6 57-11-4	Secondary	Ultra fast	7	75% by weight of ground Vultac 3 mixed with stearic acid
Vultac® TB7	Poly-tert-butylphenol disulfide	60303-68-6	Secondary	Ultra Fast	7	Nitrosamine-free vulcanizing agent
Vultac® TB710	Mixture of poly-tert-butylphenoldisulfide and stearic acid	60303-68-6 57-11-4	Secondary	Ultra Fast	7	Nitrosamine-free vulcanizing agent

Thiadiazoles

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Echo® A	A blend of esters of 2,5-dimercapto 1,3,4-thiadiazole	Proprietary	Secondary	Fast	1	Used in halogenated compounds CPE and CSM

Retarders

Diphenylamine

Trade Name	Chemical Name	CAS Registration Number	Type	Cure Speed	Form	Comments
Ekaland™ Nitroso HU	N-Nitrosodiphenylamine	86-30-6	-	-	6	Retarder used in high temperature vulcanization systems to control scorch. It is only organic acid retarder that can be used with sulfenamide accelerators.

™, ® Permission to use registered tradename(s) of products with such registration indicated has been granted by the rightful owners:

® Echo A-PMC Organometallix; Vultac-Arkema

™ Ekaland-MLPC International

Forms: 1=powder, 2=oil treated powder, 3=granule, 4=crystal, 5=crystal w/anti-caking agent, 6=dispersion in water, 7=pastille