



NATROCHEM, INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET ATLAS BURGUNDY PITCH

Atlas Burgundy Pitch is a *rosin pitch* blended from gum rosin for use in paint, rubber and adhesives. The term "pitch" usually connotes a product that is a residuum of still bottoms, but Atlas Burgundy Pitch contains no residuum products. Atlas Burgundy Pitch is used as an adhesive. It is used as an internal tackifier for rubber compounds. It is formulated using high quality raw materials according to recipe, and to meet acid number and softening point specifications.

Standard package is a 38 lb. net metal pail.

TEST	TEST METHOD	SPECIFICATION
Acid Number	QCL-8.2.4-2-4	125 – 150*
Softening Point, Ball & Ring, °F	QCL-8.2.4-2-11	140 – 160*

TYPICAL PROPERTIES

Color, Gardner, 50%	7
Specific Gravity @ 60°F	0.91*
Ash, %	0.1
Flash Point, COC, °F	370
Fire Point, COC, °F	435

* Changed from previous spec

Date of Revision: 2015-06-23

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™
Natro-Flex™ - Tar-Cel® - Natro-Cel®