

BUNA® CB 1220

Product Description

Buna® CB 1220 is a Cobalt catalysed butadiene rubber with a high 1,4-cis content and a broader molecular weight distribution with a high degree of branching. This polymer structure allows easy processing during the production of high-quality rubber goods.

The product can be used in sidewall and tread compounds for tires. Further typical applications are conveyor belts, golf balls, footwear soles, etc. Buna® CB 1220 can be blended with NR for goods having thick sections, high resistance to reversion and high abrasion resistance.

Supply Form

Bales

Polymer Properties

Property	Nominal Value with Unit	Test Method
Mooney Viscosity ML (1+4) 100 °C	40 MU	ISO 289 / ASTM D 1646
Cis 1,4 Content	> 96 %	Internal Method

Other Product Features

Property	Typical Value with Unit	Test Method
Density	0,91 g/cm ³	ASTM D 297
Packaging	35,6 kg bales wrapped in PE film; 36 bales in a metal box (1281,6 kg)	
Storage Conditions	The product should be stored dry and at temperature < 35°C. Exposure to light has to be avoided.	

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Buna® is a trademark of ARLANXEO Deutschland GmbH

Disclaimer

"ARLANXEO makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document (the "Information") about its accuracy, suitability for particular applications, or the results obtained or obtainable using the Information. Some of the Information arises from laboratory work with small-scale equipment that may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. ARLANXEO makes no warranties, express or implied, including, but not limited to, implied warranties of merchantability and fitness for a particular purpose, with respect to the Information, ARLANXEO's products listed in the Information, or the suitability of either ARLANXEO's products, or the Information, for your process or end-use application. This document and the Information shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any offer to sell, offer to purchase, or sale of ARLANXEO's products are expressly governed by ARLANXEO's general terms and conditions of sale applicable to the ARLANXEO legal entity selling, or offering to sell, any such product."

Date of Release: 19.05.2022 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.

Page 2 of 2 This document contains important information and must be read in its entirety.