



Technical Information

Neoflon® FEP NP-30

Neoflon FEP NP-30 was developed for extrusion of cable jacket, tubing, and film.

Typical properties

Melt Flow Rate, g/10 min	ASTM D-2116	2.0 – 3.6
Melting point (DSC), °C	ASTM D-2116	265 - 275
Tensile strength, MPa, min.	ASTM D-2116	20.0
Elongation, %, min.	ASTM D-2116	275
MIT Flex, cycles, avg.	ASTM D-2176	30,000

Note: Typical properties are not suitable for specification purposes.

IMPORTANT NOTICE: The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

MEDICAL USE: This product is not specifically designed or manufactured for use in medical implantation and/or dental devices. We have not tested it for such application and will only sell it for such use pursuant to contract containing specific terms and conditions required by us.

Daikin America, Inc.
20 Olympic Drive
Orangeburg, NY 10962
Customer & Technical Service 800-365-9570