



DAIKIN AMERICA, INC.
20 Olympic Drive
Orangeburg, NY 10962
Tel: (845) 365-9500
Fax: (845) 365-9515

TECHNICAL DATA SHEET

DAIKIN-POLYFLON™ PTFE M-18

Daikin-Polyflon M-18 is a polytetrafluoroethylene virgin granular fine cut resin. This general purpose molding powder has been specifically designed for use in medium to large rod and billet compression molding applications.

Typical characteristics of the resin are as follows:

CHARACTERISTIC	UNITS	VALUE	TEST METHOD
BULK DENSITY	g/l	470	JIS K6891
STD SPECIFIC GRAVITY	---	2.16	JIS K6891
TENSILE STRENGTH (min.)	MPa	35	JIS K6891
ELONGATION (min.)	%	300	JIS K6891
BREAK DOWN VOLTAGE	kV/0.1mm	11.0	ASTM D 149
SHRINKAGE	%	3.2	DAIKIN
APPEARANCE	---	WHITE POWDER	VISUAL

Note: The data listed above fall within the normal range of product, but they should not be used to establish specification limits nor be used as the sole basis of design.

SAFETY & HANDLING

Daikin-Polyflon PTFE M-18 should be handled like other Daikin-Polyflon PTFE resins. When PTFE resins are heated to temperatures above 260°C, minor amounts of decomposition products are given off. These decomposition products may be harmful and inhalation of these fumes must be avoided. Ovens, process equipment and the working area must be adequately ventilated. For further information please refer to the material safety data sheet for this product.

Rev. 02/2006