

# LEVAMELT<sup>®</sup> 700

## Grade Name

LEVAMELT<sup>®</sup> 700

## Product Description

Ethylene-vinyl acetate copolymer (EVM) with 70 wt % vinyl acetate and dusted with separating agents (silica and talc).

## Supply Form

Granules, almost colorless.

## Production Site

Dormagen, Germany

## Specifications<sup>1</sup>

Characteristics	Limits	Unit	Testing Method	Condition
Melt flow index (**)	4 ± 2	g/10 min	ISO 1133	190 °C / 2.16kg
Vinyl acetate content	70 ± 1.5	wt%	Internal Method LP 015	(VAC)
Volatile Matter	≤ 0.6	wt%	According to ISO 248/ASTM D 5668	105 °C, 6h

<sup>1</sup>For each delivery a Certificate of Analysis (CoA) will be sent, which contains the actual measured values of the specified properties for each batch.

## Typical Product Features<sup>2</sup>

Characteristics	Limits	Unit	Testing Method	Condition
Density	≈ 1.07	g/cm <sup>3</sup>	INN PV 476	
Total Ash	≤ 0.8	wt%	According to ISO 247/ASTM 5667	10min at 800 °C

<sup>2</sup>Not to be considered as delivery specification.

(\*) MFI and MFR (Melt flow rate) are similliar



**LEVAMELT<sup>®</sup> 700**

<b>Identification</b>	The bags are marked with the Levamelt <sup>®</sup> Grade name, lot number and single bag number. Additional cardboard boxes are marked with the Levamelt <sup>®</sup> Grade name only. The pallets/boxes are marked with the producer name and address, product name, lot number and net weight. All pallets/boxes are marked with a unique 20-digit code (Stock Unit Number) for traceability.
<b>Packaging</b>	The material is filled in 25 kg bags (film based on EVA-Copolymer resin, melting point 93°C, film thickness 0,13 mm), packed in cardboard boxes and delivered on a wooden pallet containing 40 boxes (net weight per pallet 1000 kg) covered by a PE stretching film.
<b>Storage Conditions</b>	Store under cool temperatures and dry conditions in original packaging. Avoid exposure to the light. Do not stack pallets/boxes at storage. The temperature for storage shall not exceed +5 °C. Keep storage to a minimum. Granules tends to block at temperatures above +5 °C or if stored improperly. For this reason, the flowability of this product is explicitly not warranted.
<b>Shelf Live</b>	36 month from date of production (see CoA) warranted under the above mentioned storage conditions. The expiration of the best before date does not necessarily mean that the product has become unusable. However, before using such a product, it is necessary that the customer check the product as to whether the Specifications of the product are still present. ARLANXEO does not assume a warranty or liability for compliance with the Specifications after Expiration of the best before date.
<b>Delivery Conditions</b>	Please find our General Conditions of Sale & Delivery at our website <a href="http://www.ARLANXEO.com">www.ARLANXEO.com</a>
<b>Document Validity</b>	This product specification becomes valid with the signature of ARLANXEO and is valid until the next update. Customers will be informed as soon as reasonably practical about changes with regards to the process, to manufacturing plant, to testing methods, etc. which, to the best of our knowledge, may affect the specified properties.
<b>Contact</b>	In case of technical questions, please get in contact with our Technical Support via the known communication channels.



# LEVAMELT<sup>®</sup> 700

**Date / Issue**

Issue number: ARL 02 / Date of issue: March 01, 2017 / Previous issue from October 10, 2016 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.

**Signature**

ARLANXEO USA LLC  
via ARLANXEO Deutschland GmbH  
BU High Performance Elastomers  
Global HSEQ  
Quality Management & Product Stewardship  
i.V.


**Date / Issue**

Issue number: ARL 02 / Date of issue: March 01, 2017 / Previous issue from October 10, 2016 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.

LEVAMELT<sup>®</sup> (EVM) is a Registered Trademark of Bayer AG, Germany

**Health and Safety Information:** Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the ARLANXEO products mentioned in this publication. For materials mentioned which are not ARLANXEO products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., *material safety data sheets and product labels*. Consult your ARLANXEO Corporation representative or contact the Product Safety and Regulatory Affairs Department at ARLANXEO.

**ARLANXEO Corporation**

111 RIDC Park West Drive · Pittsburgh, PA 15275 · Phone: 1-800-526-9377 ARLANXEO · www.US.ARLANXEO.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. As with any product, use of the products mentioned in this publication in a given application must be tested (including field testing, etc.) by the user in advance to determine suitability.

