

Product Bulletin

supresta™
BUILT-IN DEFENSE

Phosflex® 362


MARKETED BY
HARWICK STANDARD
DISTRIBUTION CORPORATION
60 S. Seiberling Street • Akron, Ohio 44305

Phosflex®
Flame Retardant Plasticizers

Chemical Name: 2-Ethylhexyl Diphenyl Phosphate

CAS #

2-ethylhexyl diphenyl phosphate 1241-94-7
Triphenyl phosphate 115-86-6



Overview

Phosflex® 362 is a highly efficient plasticizer for PVC, with very good low temperature flexibility and excellent solvating properties for fast fusion.

One of the unique characteristics of Phosflex® 362 is its ability to reduce flammability while also reducing smoke. Typically when flame retardants are used, the combustion efficiency of the compound is decreased, and as a result, smoke (incomplete combustion particles and gases) increase. Phosflex® 362 can deliver low smoke properties and effective levels of flame retardancy in many types of polymer systems, especially flexible vinyl and vinyl alloys.

Phosflex® 362 has excellent compatibility in PVC and other plastics. Formulated correctly, it performs well in vinyl composites for outdoor applications where exposure to UV irradiation and weathering is critical. Phosflex® 362 has been found useful in flame retardant foamed vinyl and vinyl alloys (PVC/nitrile rubber), calendared sheet goods, and outdoor PVC applications. In certain rubbers, it can be useful as a solvating material to improve the tactile feel and flexibility of elastomeric composites. Phosflex® 362 also has the advantage of FDA approvals for certain food packaging applications.

Phosflex® Product Selector

	Key applications	Key characteristics
4	<ul style="list-style-type: none"> Primary plasticizer for nitro-cellulose, chlorinated rubber Anti-foam agent 	<ul style="list-style-type: none"> Low viscosity Low density
31L	<ul style="list-style-type: none"> PVC film and sheet compounds Dispersant for plastisols 	<ul style="list-style-type: none"> Low color Blendable with non-FR plasticizers
41L	<ul style="list-style-type: none"> PVC film and sheet compounds Dispersant for plastisols 	<ul style="list-style-type: none"> Low color Blendable with non-FR plasticizers
71B	<ul style="list-style-type: none"> Flame retardant plasticizer for PVC 	<ul style="list-style-type: none"> Excellent flame retardant properties Low volatility
362	<ul style="list-style-type: none"> Flame retardant plasticizer for PVC alloys 	<ul style="list-style-type: none"> Low temperature and low smoke Excellent vinyl solvating properties Approved for packaging materials in food contact
390	<ul style="list-style-type: none"> Flame retardant plasticizer for PVC sheets and coatings 	<ul style="list-style-type: none"> Excellent low temperature flexibility Low smoke, good weathering properties
314, 318, 321, 327	<ul style="list-style-type: none"> Blended plasticizer for film and sheet vinyl goods 	<ul style="list-style-type: none"> High efficiency High solvating

Key Applications

Formulations for Flexible Suspension PVC at 50 phr Plasticizer

	1	2	3	4	5
PVC Geon (103EP)	100	100	100	100	100
CaCO ₃	50	50	50	50	50
Zinc Borate (Firebrake ZB)		3	6	3	6
ATH (Hydral 710)				20	40
Plasticizers	50	50	50	50	50
ESO (Plastoflex 2307)	5	5	5	5	5
Stabilizers (Ba/Zn mixed metals)	5	5	5	5	5
Totals (parts)	210	213	216	233	256

These five formulations represent basic formulation and component variations typically seen for FR-PVC. The resultant flammability and physical properties are shown in the following tables with comparisons to similar flame retarded vinyl systems.

Phosflex® 362 in PVC Suspension Resin (GEON 103EP)

Component	Additive phr	Tensile Properties			Hardness		LOI 100 Mils	UL-94 1.6mm
		Strength psi (MPa)	E Mod. psi (MPa)	Elong. %	Shore "A" Initial	Creep (15 sec.)		
DIDP	50	1844(12.7)	858(5.9)	426	88	85	23	FAIL
ZB	3	2018(13.9)	907(6.2)	461	88	84	23.2	FAIL
ZB	6	1824(12.6)	906(6.2)	417	90	86	23.2	FAIL
ZB/ATH	3/20	1635(11.3)	945(6.5)	359	91	86	23.6	FAIL
ZB/ATH	6/40	1715(11.8)	1081(7.4)	374	93	89	25	FAIL
Phosflex® 362	50	1389(9.6)	602(4.1)	394	82	78	27	V-0
ZB	3	1365(9.4)	610(4.2)	387	82	78	27.6	V-0
ZB	6	1284(8.8)	629(4.3)	359	82	78	27.6	V-0
ZB/ATH	3/20	1319(9.1)	706(4.9)	366	83	80	28.2	V-0
ZB/ATH	6/40	1227(8.5)	784(5.4)	345	87	84	30.4	V-0

Typical Properties

Physical appearance	Clear, transparent liquid
Phosphorus content, wt. %	8.5
Specific gravity, 20°C/20°C	1.090
Density @ 20°C, lbs/gal	9.1
kg/m ³	1090
Viscosity @ 25°C, mPa.s	18
Acidity, as phosphoric acid, %	0.01
Water content, wt. %	0.10
Color, APHA	40


Safety & Handling

Consult the Material Safety Data Sheet for this product.

Shipping Information

Available in bulk tank trucks, isocontainers, 2,200 lb totes, and 480 lb drums.

Thermogravimetric Analysis: Phosflex® 362 (10°C rise/minute in nitrogen)



2% wt. Loss	182°C
5% wt. Loss	198°C
10% wt. Loss	211°C

For more information about our products and to place an order, please contact one of Supresta's regional sales offices.

AMERICAS REGIONAL SALES OFFICE
Ardsley Park at 420 Saw Mill River Road
Ardsley, New York 10502 USA
914.269.5900, 800.666.1200
fax 914.674.9735

ASIA PACIFIC REGIONAL SALES OFFICE
12/B, Sun Tong Plaza, No.55 Huai Hai Road West
Shanghai 200030 China
86 21 5298 9058
fax 86 21 5298 9352

EUROPEAN REGIONAL SALES OFFICE
Hoefseweg 1, PO Box 2501
3800 GB Amersfoort, The Netherlands
31 33 4534 575
fax 31 33 4534578

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable as of the date of publication. However, no warranty is made as to the accuracy of and/or sufficiency of such information and/or suggestions as to the merchantability or fitness of the product for any particular purpose, or that any suggested use will not infringe any patent. Nothing herein shall be construed as granting or extending any license under any patent. Buyer must determine for itself, by preliminary tests or otherwise, the suitability of this product for its purposes, including mixing this product with other products. The information contained herein supersedes all previously issued bulletins on the subject matter covered.