



**NATROCHEM, INC.**  
P.O. BOX 1205  
SAVANNAH, GA 31402  
(912) 236-4464 FAX: (912) 236-1919  
[www.natrochem.com](http://www.natrochem.com)

## **DATA SHEET**

### **SR 350W DLC-R-60**

SR 350W DLC-R-60 is a trimethylol propane trimethacrylate, silicon dioxide blend used for peroxide cures of BR, CR, EPM, EPDM IIR, IR and NBR. A vulcanizing co-agent with peroxide cure, it plasticizes during mixing, and hardens on curing.

<b>TEST</b>	<b>TEST METHOD</b>	<b>SPECIFICATION</b>
Actives Content, %	QCL-8.2.4-2-1	58 - 62
Carrier Content, %	QCL-8.2.4-2-1	38 - 42

#### **TYPICAL PROPERTIES**

Actives Content, %		60
Carrier Content, %		40
Specific Gravity (Apparent)		1.18
Packaging	40# Net, Multi-wall Bags	
Color		Off-White

Date of Revision: 09/18/03

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

#### **OTHER NATROCHEM PRODUCTS**

**DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™**  
**Natro-Flex™ - Tar-Cel® - Natro-Cel®**