



NATROCHEM, INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET TARENE™ 40

Tarene 40 is a low-cost, dark, non-staining, thermoplastic oleo-resinous product having a naval stores base. The performance properties are comparable or superior to pine tar. Tarene 40 finds its widest application as a plasticizer, tackifier, and processing aid in rubber compounding. Other potential uses include adhesives, tar modifications, epoxy extension, coatings, mastics, and use as a low-cost acid for emulsions.

TEST	TEST METHOD	SPECIFICATIONS
Acid Number	QCL-8.2.4-2-4	20 - 40
Viscosity, SFS@ 122°F	QCL-8.2.4-2-5	150 - 225
Specific Gravity@ 80°F	QCL-8.2.4-2-12	0.950 - 1.000
Moisture, %	QCL-8.2.4-2-7	1.0 Max
Heat Loss, 2 hrs@ 105°C	QCL-8.2.4-2-9	6.0 Max
Ash, %	QCL-8.2.4-2-8	1.25 Max

TYPICAL PROPERTIES

Acid Number	30
Viscosity, SFS@ 122°F	175
Specific Gravity@ 80°F	0.975
Moisture, %	0.1
Heat Loss, %	1.5
Ash, %	0.4

Date of Revision: 12/9/02

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

DLC® - Galax® - Rosin Oils - Rosin Pitches - Tarene™

Natro-Flex™ - Tar-Cel® - Natro-Cel®